



TECHNICAL DATA SHEET

CAT 200

● SUMMARY

HARDENER

● USE

Hardener used for the water base polyurethane adhesive serie **ECOSAR MW 135**, in order to improve the hydrolysis and heat resistance.

● CHARACTERISTICS

- Appearance	transparent honey
- Density	approx.: 1,15 g/cm ³ at 23°C
- Content NCO	21,8 +/- 1
- Viscosity 23°C	1250 +/- 500 mPa s

● APPLICATION

Hardener **CAT 200** has to be used together with water base polyurethane adhesive serie **ECOSAR MW 135** usually in the percentage of 2% in order to improve the hydrolysis and heat resistance. In case it is necessary an higher resistance the percentage can reach the 3% maximum.

● STORAGE

The expire date of the product shown on the label is valid for products if kept away from direct heat and cold and at standard storage conditions (minimum temperature 4°C to maximum 40°C).
Exceeding the expiration date does not necessarily mean that the product no longer meets the specifications or values set.
However, before using this product after the expiration date, Kenda Farben recommends checking whether it still meets the reference specifications or values. Kenda Farben will not be in any way responsible for failure to comply with specifications or values set after the deadline or due to incorrect storage that can shorten the life of the product.

● NOTE

Keep away from freeze and heat.
Keep the containers well sealed.

This information is to the best of our knowledge true and accurate. However, all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

29-11-2024 GA/pm