



## TECHNICAL DATA SHEET

# ECOSAR 116

### ● SUMMARY ADHESIVE IN WATER DISPERSION, WITH A BASIS OF SYNTHETIC LATEX

● **USE** It is particularly suitable for leathers goods, for coupling of leather and synthetic material. It can be applied both by gun-spray and roll-machine.

● <b>CHARACTERISTICS</b>	– Appearance	ivory white liquid
	– Viscosity: (Brook, RVT, 20°C)	160-300 cps (G2 – V20)
	– pH value	between 8 and 9
	– Solids content	54 +/- 3
	– Specific weight at 20°C	1,00 +/- 0,01

- **APPLICATION**
- Use the product under the following conditions:
    - ambient temperature of the adhesive and the materials to be glued, around 20 - 22°C
    - humidity of the materials to be glued 8 - 10%
    - relative humidity of the air 65 - 75%
  - **ECOSAR 116** has to be applied on both surfaces to be bond
  - leave to dry for a minimum of 10 minutes, then press the two surfaces together
  - during the spraying operation it is necessary to adjust the distance of spraying gun in order to obtain an homogeneous spraying
  - open time 8 hours

**Notes:** it is suggested to use the adhesive at temperatures not lower than 18°; in case the material is stocked in cold ambients, recondition before using

