



QUALITY MANAGEMENT
SYSTEM
CERTIFIED ISO 9001

TECHNICAL DATA SHEET

Series

16

SAR 137

● SUMMARY

ADHESIVE FOR DIRECT INJECTION OF TR RUBBER

● CHARACTERISTICS

- Adhesive TR rubber based momocomponent
- Colour transparent hazel
- Viscosity Ford cup n. 6 at 20°C 60" +/- 5"
- Specific weight at 20°C 0,88 +/- 0,01
- Dry residue 39 +/- 1%
- Solvents content according to current law regulations
- Flammable

● APPLICATION

- Apply adhesive through the use of a roller machine or manually by pad
- wait 20 minutes until complete drying
- to proceed with the injection TR rubber; where appropriate the operation of injection can be even after days as from the application

Notes: it is suggested to use the adhesive at temperatures not lower than 18°; in case the material is stocked in cold ambients, recondition before using

● SOLVENTS

Use **SOLVENTE 31708** for thinnings

● PACKING

Tin of Kg. 15 net weight

● STORAGE

Shelf life: about 24 months if stored in well closed original packings at a temperature of 15 - 25°C.

This information is to the best of our knowledge true and accurate. However, all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

08-04-2015 RM/pm