



● SUMMARY

MELTING POLYAMIDIC GRANULATED ADHESIVE

● CHARACTERISTICS

– Adhesive	thermo-melted
– Colour	straw-yellow
– Melting point (°C)	102 - 105
– Fuse viscosity at 160°C	900 - 1.100 m.Pas
– Cementing time	fast (1 - 2 seconds)
– Working temperature (°C)	135 – 150
– Chemical name	polyamidic adhesive

● DESCRIPTION

Low powder formation, granulated adhesive, having a regular parallelepipedon shape, without impurity; suitable to be employed on folding machines equipped with feeding tank.

● APPLICATION

– Machines equipped with feeding tank

Notes: it is suggested to use the adhesive at temperatures not lower than 18°; in case the material is stocked in cold ambients, recondition before using

● SOLVENTS

It is not necessary

● PACKING

Bag of Kg. 20 n.w.

● STORAGE

Shelf life: about 24 months if stored in well closed original packings in a dry and airy place.
Keep from freezing and extreme heat.

This information is to the best of our knowledge true and accurate. However, all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

21-04-06 RM/pm