



TECHNICAL DATA SHEET

Series

16

SAR 303

● SUMMARY

POLYURETHANE PRIMER HAVING HIGH SOLID CONTENTS

● CHARACTERISTICS

- Adhesive monocomponent polyurethane
- Colour opalescent light
- Viscosity at 20°C 26" Ford cup n° 6
- Open time fast
- Specific weight at 20°C 0,85 +/- 0,01
- Reactivation temperature (°C) 60 - 70
- Solvents content according to current law regulations
- Flammable
- Chemical name polyurethanes solution in organic solvents

● APPLICATION

- Apply **SAR 303** added by 5% activator DESMODUR RFE or DESMODUR RC
- drying time 5 - 10 minutes
- proceed applying the final adhesive SAR 306 or SAR 22

Notes: it is suggested to use the adhesive at temperatures not lower than 18°; in case the material is stocked in cold ambients, recondition before using

● SOLVENTS

Use **SOLVENTE 31714** for thinnings

● PACKING

Tin of Kg. 15 net weight

● STORAGE

Shelf life: about 24 months if stored in well closed original packings in a dry and airy place.
Keep from freezing and extreme heat.

This information is to the best of our knowledge true and accurate. However, all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

02-07-08 RM/pm