



TECHNICAL DATA SHEET

Series **16**

**SAR 600**

● SUMMARY

NEOPRENE ADHESIVE FOR “AGO” WORKING

● CHARACTERISTICS

- Adhesive monocomponent polychloroprene
- Colour yellow
- Viscosity at 20°C 2.800 +/- 200 cps
- Open time 30 - 60 minutes
- Specific weight at 20°C 0,850 +/- 0,020
- Reactivation temperature (°C) 70 - 80
- Solvents content according to current law regulations
- Flammable
- Chemical name polychloroprene in organic solvents

● APPLICATION

- Duly prepare the surfaces to be joined
- apply the adhesive and let dry for about 20 minutes
- join the parts and press at 6 Kg./cm<sup>2</sup> for about 10 seconds

**Notes:** it is suggested to use the adhesive at temperatures not lower than 18°; in case the material is stocked in cold ambients, recondition before using

● SOLVENTS

Use **SOLVENTE 31700** for thinnings

● PACKING

Drum of Kg. 15 net weight

● STORAGE

Shelf life: about 24 months if stored in well closed original packings in a dry and airy place.  
Keep from freezing and extreme heat.

This information is to the best of our knowledge true and accurate. However, all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

21-04-06 RM/pm