



● *SUMMARY*

**MONOCOMPONENT NEOPRENE ADHESIVE FOR THE PRODUCTION OF  
INSOLES BY “ ONE-WAY “ METHOD**

● *CHARACTERISTICS*

- Adhesive monocomponent polychloroprene
- Colour light yellow
- Viscosity at 20°C 70” +/- 5” Ford cup n° 8
- Open time long
- Specific weight at 20°C 0,86 +/- 0,01
- Reactivation temperature (°C) /
- Solvents content according to current law regulations
- Flammable
- Chemical name polychloroprene in organic solvents

● *APPLICATION*

- Apply on the cellulosic material a uniform coating of adhesive by roller traditional machine or automatic machine (type “ OMAV – REFI “ etc.)
- pass in the drying
- unit, then couple the paints of fiberboard carton and starting the final pressing
- excellent even for the cleaning tongue position

**Notes:** it is suggested to use the adhesive at temperatures not lower than 18°; in case the material is stocked in cold ambients, recondition before using

● *SOLVENTS*

Use **SOLVENTE 31733** for thinnings

● *PACKING*

Tin of Kg. 15 net weight

● *STORAGE*

Shelf life: about 24 months if stored in well closed original packings in a dry and airy place.  
Keep from freezing and extreme heat.

This information is to the best of our knowledge true and accurate. However, all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

12-09-2019 RM/pm