



TECHNICAL DATA SHEET

Series

16

SAR 76 A

● SUMMARY

NEOPRENE ADHESIVE FOR GENERAL USE

● CHARACTERISTICS

- Adhesive monocomponent polychloroprene
- Colour deep yellow
- Viscosity at 20°C 53" Ford cup n° 8
- Open time 30 minutes
- Specific weight at 20°C 0,87 +/- 0,02
- Reactivation temperature (°C) /
- Solvents content according to current law regulations
- Flammable
- Chemical name polychloroprene in organic solvents

● APPLICATION

- Apply the adhesive on the interested surfaces by means of an horse air brush or a buttering spatula
- once the solvent evaporation has been completed, proceed in coupling the parts, paying attention to start from the center up to the periphery, either by rolling or by evenly hammering. This in order to avoid any blister
- after a 48 hours period from the coupling is possible to measure the maximum adhesion point

Notes: it is suggested to use the adhesive at temperatures not lower than 18°; in case the material is stocked in cold ambients, recondition before using

● SOLVENTS

Use **SOLVENTE 31700** for thinnings

● PACKING

● STORAGE

Shelf life: about 24 months if stored in well closed tins at 15 - 25°C.

This information is to the best of our knowledge true and accurate. However, all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

21-04-06 RM/pm